



STRAHL & PITSCHE

230 Great East Neck Rd., West Babylon, NY 11704, U.S.A.

Phone: 631.587.9000

Fax: 631.587.9120

www.spwax.com

Synthetic Beeswax

SP-755

SP-755P

| Test | Method | Specification |
|---------------|----------------------|----------------|
| Color | Visual | Off White |
| Melting Point | Current NF monograph | 74.0 – 78.0 °C |
| Acid Value | Current NF monograph | 19.3 - 24 |
| Ester Value | Current NF monograph | 69 - 77 |

J. Jodice 7/1/09

Signature

Date

Version: A
Supersedes: None